



EXTENDED COMMERCIAL ROOF-COATING WARRANTY SCHEDULE

APPLICATION GUIDE

E-las•tek White Elastomeric Coatings	2 or more Coats *			3 or more Coats *		
	Minimum coverage sq.ft./gal.	Minimum dry ** mils	Warranty period (years)	Minimum coverage sq.ft./gal.	Minimum dry ** mils	Warranty period (years)
#100 Solar Mastic	100	18-20	6	100	27-30	8
#120 Solar Tek Extreme	100	18-20	7	100	27	10
#109 Solar Magic	100	18-20	5	--	--	--

LEGEND:

* Yield approximately 10 dry mils per coat @ 100 sq. ft. per gallon application

** Minimum dry thickness—application methods may cause uneven coating thickness. Apply sufficient coating to meet minimum standards. Applicator should sample wet and dry mils during application to assure minimum requirements are met.

Number of coats applied is not critical; dry-coating thickness is critical.

Other **E-las•tek** topcoats and asphaltic coatings distributed by SEPI under the **E-las•tek** name are NOT eligible for extended Warranty.

SEPI reserves the right to check dry-coating thickness prior to issuing a Warranty, and/or in the event of a reported Warranty failure. The assumed rate of coating erosion is no more than 0.5 mils per 12-month period.

Adequate coating thickness is critically important to assuring service life Warranty!